



Achieve the innovative value of paint

## JIAZHI® Easy-cleaning functional resin

### Model number

JIAZHI®JZ-9546

### Specification

Composition	Fluorosilicon modified hydroxyl acrylic resin solution
Appearance	Slight yellowish to yellowish liquid
Solvent	BAC/ PMA/ Xylene
Content	50±3%(105℃ 2h)
Density	1.05-1.09g/ml(25±1)℃
Viscosity	100-1000mPa·s (Rotating viscometer)(25±0.2)℃
Hydroxyl value	76±5 mg KOH/g (Theoretical value of solid resin)

Note: This datasheet is intended to give typical results, not standard. Subject to COA.

### Application system

Solvent-based

### Properties

- Increase slip. Improve hydrophobicity and oleophobicity.
- Provide anti-marker wiping performance.
- Provide lotus.
- Excellent flexibility.
- Excellent scratch and wear resistance.
- Compared with anti-graffiti additive, better anti-graffiti effect and solvent-resistant wiping performance.
- Excellent weather resistance.

### Recommended formula

#### 1. Suggestion for PU varnish formulation

	Material	Dosage%
Part A	JZ-9546	76.0
	PMA	22.65-22.74
	Dryer(1%)	1.0
	WE-D8920BR(leveling agent)	0.25
	WE-D980(defoamer)	0.01-0.1
	Total	100
Part B	N3390	11.5

Note:

1. Usage recommendation for defoamer  
Add WE-D980 with 0.01% to PU varnish and no affecting of compatibility.  
Can increase the addition to 0.1% of WE-D980 to color paint.
2. NCO% of N3390=19.6, produced by Covestro, Germany.
3. The mixed part A and B should be used up within 5-7 hours in a sealed container. Otherwise, the mixed material will be gelled.
4. Suggest dry it at 80℃ for 1h or 150℃ for 5min.

### Storage stability

Keep intact 36 months in original package. Products beyond the storage period may continue to be used after inspection. The container must be closed immediately after use.

### package

25KG / 180KG

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above mentioned statements have to be adjusted to the circumstances of the processor.